

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-310321

(43)Date of publication of application : 04.11.1994

(51)Int.Cl.

H01F 1/34
C01G 49/00
C04B 35/38

(21)Application number : 05-095791

(71)Applicant : MATSUSHITA ELECTRIC IND CO
LTD

(22)Date of filing : 22.04.1993

(72)Inventor : MATSUTANI SHINYA
INOUE OSAMU
KUGIMIYA KOICHI
ISHII OSAMU
AONO YASUYUKI
SUZUMURA MASAKI**(54) OXIDE MAGNETIC SUBSTANCE MATERIAL****(57)Abstract:**

PURPOSE: To obtain an oxide magnetic substance material which is excellent in the temperature characteristic of a magnetic loss and whose magnetic loss is low by a method wherein at least CaO and SiO₂ in a specific amount and at least one kind of a specific metal oxide are contained in an MnZn-based ferrite within a specific composition range.

CONSTITUTION: Fe₂O₃ at 61mol% or higher and 67mol% or lower, MnO at 3mol% or higher and 36mol% or lower and ZnO at 0mol% or higher and 30mol% or lower are contained as main compositions, and 0.05≤CaO≤0.5wt.% and 0.005≤SiO₂≤0.2wt.% are contained as subcomponents. In addition, an oxide magnetic substance material is constituted as a sintered body which contains at least one kind of a metal oxide out of TiO₂, CoO, CuO, SnO₂ and NiO at 0.005wt.% or higher and 0.5wt.% or lower. Thereby, it is possible to obtain the material whose magnetic loss is low and whose temperature characteristic is excellent. A switching power supply using it generates little heat, is highly efficient and displays the small danger of a temperature runaway.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of

rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office